





T61

Material Data Sheet

NON GLUED LAMINATE FLOORS		$\Delta L_w = 20\text{dB}$	100% Natural and Sustainable Product Impact Noise Reduction and Thermal Insulation Properties High Durability and Long Term Resilience High Performance with Reduced Thickness Tested according to MMFA/EPLF requirements Group 1
GLUED DOWN WOOD FLOORS		$\Delta L_w = 26\text{dB}$	
GLUED DOWN WOOD FLOORS PERFORATED		$\Delta L_w = 18\text{dB}$	
CERAMIC OR NATURAL STONE FLOORS		$\Delta L_w = 16\text{dB}$	



PRODUCT DESCRIPTION

Agglomerated cork underlay for impact noise and thermal insulation.



THERMAL PROPERTIES

Thermal Conductivity: 0,04 W/mK ⁽¹⁾

⁽¹⁾ ISO 8301



PHYSICAL AND MECHANICAL PROPERTIES

Specific Weight ⁽¹⁾	Tensile Strength ⁽¹⁾	Compression at 0,7MPa ⁽¹⁾	Recovery after 0,7MPa ⁽¹⁾
150 - 200 Kg/m ³	> 200 KPa	30%	> 70%

⁽¹⁾ ISO 7322



ACOUSTICAL RESULTS

Flooring	Thickness (mm)	ΔL_w (dB) ⁽¹⁾	IIC (dB) ⁽²⁾
Non Glued Laminate	2	20	54
Glued Down Wood	3	26	59
	3 perforated	18	51
Ceramic (or Natural Stone)	5	16	50

⁽¹⁾ ISO 10140-3 and ISO 717-2 • ⁽²⁾ ASTM E492-09 & ASTM E989-06



STANDARD DIMENSIONS


Thickness (mm)	2	3	3 perforated	5
Width (m) x Length (m)	1 x 10	1 x 10	0,5 x 10	1 x 10





ACOUSTICAL RESULTS

Test procedure according to ISO 10140-1:2010; ISO 10140-3:2010; ISO 10140-4:2010 and ISO 717-2:2013 standards.




$L_{n,r}$ - Normalized impact sound pressure level of the reference floor with the floor covering under test;
 $L_{n,r,0}$ - Normalized impact sound pressure level of the Lab reference floor;
 ΔL_w - Impact sound pressure level reduction index of the covering under test, on a normalized floor;

$L_{n,r,0}$ (dB)
 $L_{n,r}$ (dB) - 2mm - Laminate
 $L_{n,r}$ (dB) - 3mm - GDW*
 $L_{n,r}$ (dB) - 3mm perforated - GDW*
 $L_{n,r}$ (dB) - 5mm - Ceramic

*Glued Down Wood

TEST APPARATUS (ΔL_w & IIC)




01. Floor covering composed by glued down wood, non glued laminate floor or ceramic or natural stone tiles
 02. Agglomerated cork resilient layer - T61
 03. Reinforced concrete slab of thickness 140mm

Ref. Test Report	Thickness	Flooring	$L_{n,r,w}(C_{l,r})$	$\Delta L_w(C_{l,\Delta})$
SRLC/06/5L/3676/1a	2 mm	Non Glued Laminate	58 (0) dB	20 (-11) dB
SRLC/06/5L/3676/1a	3 mm	Glued Down Wood	52 (1) dB	26 (-12) dB
ACL034/16	3 mm perforated	Glued Down Wood	60 (0) dB	18 (-11) dB
SRLC/06/5L/3676/1a	5 mm	Ceramic (or Natural Stone)	62 (0) dB	16 (-11) dB



ACOUSTICAL RESULTS

Test procedure according to ISO 10140-1:2010; ISO 1040-3:2010 and ISO 10140-4:2010 standards.
 Normalized impact sound pressure level and IIC rating determined according ASTM E492-09 and ASTM E989-06 standards.



L_{ref} - Normalized impact sound pressure level of the reference floor with the floor covering under test;
 $L_{ref,c}$ - Normalized impact sound pressure level of the Lab reference floor;

L_{ref} (dB)
 $L_{ref,c}$ (dB) - 2mm - Laminate
 $L_{ref,c}$ (dB) - 3mm - GDW*
 $L_{ref,c}$ (dB) - 3mm perforated - GDW*
 $L_{ref,c}$ (dB) - 5mm - Ceramic


*Glued Down Wood

Thickness	Flooring	IIC _c
2 mm	Laminate	54 dB
3 mm	Glued Down Wood	59 dB
3 mm perforated	Glued Down Wood	51 dB
5 mm	Ceramic (or Natural Stone)	50 dB




PHYSICAL AND MECHANICAL PROPERTIES

LOAD DEFLECTION



CREEP DEFLECTION @ 0,0045MPa (% OF START HEIGHT)



Note: Following ISO8013-1998 measured in Cantilever Test System

DYNAMIC STIFFNESS


Test procedure according ISO 9052-1 and ISO 7626-5 standards.

Thickness (mm)	Dynamic Stiffness (MN/m ³)
2	98
3	96
5	93



INSTALLATION

GLUED FLOORS



01.

Reinforced
concrete slab

02.

Adhesive


03.

Agglomerated cork
resilient layer - T61

04.

Floor covering
composed by glued
down wood, ceramic
or nature stone

NON GLUED FLOORS



05.

Perimeter insulation
barrier

06.

Vapor
barrier

07.

Floor covering
composed by
non glued
laminate floor

NON GLUED LAMINATE FLOORS		$\Delta L_w = 20\text{dB}$
GLUED DOWN WOOD FLOORS		$\Delta L_w = 26\text{dB}$
GLUED DOWN WOOD FLOORS PERFORATED		$\Delta L_w = 18\text{dB}$
CERAMIC OR NATURAL STONE FLOORS		$\Delta L_w = 16\text{dB}$ 

T61

UNDERLAY

General Installation Instructions

The following installation instructions are recommended by Amorim Cork Composites, but are not intended as a definitive project specification. They are presented in an attempt to be used with recommended installation procedures of the flooring manufacturers.

Room Conditions

Temperature > 10°C / Room moisture content < 75%.

Subfloor

All subfloor work should be structurally sound, clear and level. The moisture content of the subfloor should not be more than 2.5% (CM) by weight measured on concrete subfloors.

Vapor Insulation Barrier (only for Non Glued Floors)

PE (Polyethylene) vapor insulation barrier covering the entire flooring area, minimum 50mm wide vertically around the perimeter of the entire floor MUST be installed prior to the Acousticork T61.

Install by overlapping (minimum 100mm) the PE foil, and use an adequate tape to adhere/fix it, if necessary. After completion, PE foil should cover the entire concrete area without gaps. Never mechanically fasten the PE foil barrier with screws, nails or staples as this will severely diminish the performance of the insulation barrier.

Installation Instruction for Acousticork T61

Unpack the Acousticork T61 at least 24h before the installation and store it in the room where the installation will take place. Cut the T61 to desired length and install directly over the entire floor pulled 30mm up the walls with crown of the rolled materials up (Acousticork label side down), removing all trapped air. After completion, the T61 should cover the entire flooring area without gaps and with joints butted tight and preferably taped.

Tested according to MMFA/EPLF requirements Group 1

Final Flooring

Always follow manufacturers recommended installation instructions.

Recommended Adhesives:


Wood floor to Acousticork: Water-Based Emulsion/ Polyurethane Glue;

Vinyl and linoleum to Acousticork: Water-Based Emulsion/ Synthetic Resin Glue;


Ceramic to Acousticork: Flexible Cement Glue;

Acousticork to slab/screed: Water-Based Emulsion/ Acrylic Adhesives;

Application Process



1. Vapor insulation barrier application; 2. Perimeter barrier application; 3. Underlay application; 4. Tape application in joints between rolls; 5. Final floor application; 6. Perimeter insulation barrier cut.



1. Perimeter barrier application; 2. Underlay application (glued); 3. Final floor application (glued); 4. Perimeter insulation barrier cut.

Important Notes

Never mechanically fasten the Acousticork T61 to the flooring floor as this will severely diminish its acoustical value.

For detailed installation instructions, please contact us.